

COMPOUND SEMICONDUCTOR CRYSTAL GROWTH METHOD

COMPOUND SEMICONDUCTOR CRYSTAL GROWTH METHOD

Patent Number: JP5074717
Publication date: 1993-03-26
Inventor(s): OTSUKA NOBUYUKI
Applicant(s): FUJITSU LTD
Requested Patent: ☐ JP5074717
Application Number: JP19910230656 19910911
Priority Number(s):
IPC Classification: H01L21/205; B01J23/38; C30B25/14; C30B29/40
EC Classification:
EC Classification:
Equivalents:

Abstract

PURPOSE: To epitaxially grow an atomic layer of good quality using a small quantity of raw gas by enhancing the reactive efficiency of the raw gas by introducing a catalyst into a growth device.

CONSTITUTION: A substrate 3 is heated up using a high frequency heater 4. After a quartz reaction tube 1 has been purged by feeding hydrogen gas into it through a valve 7, $(\text{CH}_3)_3\text{Ga}$ is vaporized using a bubbler 8, and the $(\text{CH}_3)_3\text{Ga}$ is fed into the quartz reactor tube 1 through a switching valve 5. Then, after the quartz reaction tube 1 has been purged by feeding hydrogen gas again, AsH_3 is fed through a switching valve 6, and the catalyst 11 introduced into a growth device is heated up using a power source 12. As a result, the partial contact of the AsH_3 to be fed as the raw material of arsenic, is accelerated by a catalytic action, and the feeding efficiency of arsenic can be improved. Accordingly, an atomic layer can be grown by a little feeding quantity of AsH_3 .